



11/27/00

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Patent Application Transmittal

Docket No. PER0014US

BOX PATENT APPLICATION

Assistant Commissioner for Patents
Washington, D.C. 20231Crompton Corporation
199 Benson Road
Middlebury, CT 06749

Sir:

Date: November 27, 2000

Transmitted herewith for filing is the Patent Application of:

Inventors: **DENIS GHESQUIERE AND RÉMY DUMONT**
 For: **PROCESS FOR THE MANUFACTURE OF POLYURETHANE FOAM, AMINE
 POLYESTERPOLYOL USED IN THIS PROCESS AND FOAM OBTAINED**

Enclosed are:

- ☐ _____ sheets of drawings.
☐ An assignment of the invention to Crompton Corporation, Middlebury, CT 06749.
☐ A certified copy of a _____ application.
☒ Declaration and Power of Attorney
☐ Executed. ☒ Unexecuted.
☐ Information Disclosure Statement with copies of cited references.
☐ Associate Power of Attorney.
☒ Certificate of translation.

JC912 U.S. PTO
 09/723034
 11/27/00

The filing fee has been calculated as shown below:

	Claims Filed	Extra Claims	Rate	Fee
Basic Fee				\$710.00
Total Claims	-31	11	X \$18.00	\$198.00
Independent Claims	-3	0	X \$80.00	\$
<input type="checkbox"/> Multiple dependent claims presented			+ \$270.00	\$
Total Fee				\$908.00

- ☒ Please charge Deposit Account No. 23-2656 in the amount of \$908.00 A duplicate copy of this sheet is enclosed.
- ☒ The Commissioner is hereby authorized to charge payment of the following fees associated with this communication or credit any overpayment to Deposit Account No. 23-2656: any additional filing fees required under 37 CFR 1.16 and any patent application processing fees under 37 CFR 1.17. A duplicate copy of this sheet is enclosed.
- ☒ The Commissioner is hereby authorized to charge payment of the following fees during the pendency of this application or credit any overpayment to Deposit Account No. 23-2656: any patent application processing fees under 37 CFR 1.17 and any filing fees under 37 CFR 1.16 for presentation of extra claims. A duplicate copy of this sheet is enclosed.

CERTIFICATE OF MAILING

I hereby certify that, on the date shown below, this correspondence is being deposited with the United States Postal Service in an envelope addressed to Box Patent Application, Assistant Commissioner for Patents, Washington, DC 20231 as "Express Mail Post Office to Addressee".

Mailing Label No. HB355707220USon November 27, 2000

Name of person mailing paper

Shirley S. Ma
 Signature

Respectfully Submitted,

By: Shirley S. Ma

Attorney: Shirley S. Ma
 Registration No. 44,216
 Tel.: 203-573-3313

IN THE MATTER OF NATIONAL PHASE PROCESSING
IN : THE UNITED STATES OF AMERICA
OF THE INTERNATIONAL PATENT APPLICATION
PCT/FR 99/01176
FILED ON : MAY 18, 1999
THE INVENTION OF :
GHESQUIERE Denis
29, rue Madeleine Fosse
27370 TOURVILLE LA CAMPAGNE, FRANCE

DUMONT Rémy
37, rue du Point du Jour
27370 THUIT SIGNOL, FRANCE

I, John Neil Albert SWEENEY BSc, PhD, Dip. Trans.IoL
translator to RWS Group plc, of Europa House, Marsham Way, Gerrards Cross,
Buckinghamshire, England, do hereby declare that I am well acquainted with the English and
French languages and that the accompanying translation is a translation made by me of the
above International Patent Application. To the best of my knowledge and belief, this is a true
translation.



J. N. A. SWEENEY

For and on behalf of RWS Group plc

Dated this 2nd day of November 2000

**PROCESS FOR THE MANUFACTURE OF POLYURETHANE FOAM, AMINE
POLYESTERPOLYOL USED IN THIS PROCESS AND FOAM OBTAINED**

The present invention relates to a process for the manufacture of a polyurethane foam by reaction of a polyol with a polyisocyanate, in which process a tertiary amine is used as catalyst and in which process an expansion agent or foaming agent, such as water, for example, is used.

It is well known to use one or more tertiary amines to catalyze a first reaction: that of at least one polyol with at least one polyisocyanate. Furthermore, in the case where water is used as foaming agent, the tertiary amine(s) is (are) capable of catalyzing a second reaction: that of water with the free isocyanate functional groups, which reaction results in the evolution of carbon dioxide gas which serves for the expansion of the foam. Several known techniques exist for the preparation of polyurethanes. According to a first technique, at least one polyetherpolyol and/or at least one polyesterpolyol is reacted with at least one polyisocyanate, so as to obtain a prepolymer comprising free isocyanate groups, and then the prepolymer obtained is reacted with an additional amount of polyol(s). Another well known technique is the so-called "one shot" technique, where all the ingredients are introduced, separately or selectively premixed according to their compatibility, into the mixing head.

The known tertiary amines can promote the first reaction and/or the second reaction to variable extents. When one of the reactions is not catalyzed or is insufficiently catalyzed, it is then necessary to use another catalyst for the other reaction. This other catalyst can be an organometallic derivative, such as stannous octoate or dibutyltin dilaurate, known for preferentially catalyzing the isocyanate polyol reaction. The use is therefore being attempted of tertiary amines which satisfactorily catalyze both reactions. It is known to use tertiary amines, such as

N-ethylmorpholine, dimethylbenzylamine, triethylene-diamine and hexadecyldimethylamine, these tertiary amines being introduced as such into the reaction mixture.

5 However, these tertiary amines have a disadvantage: they are volatile, have a very unpleasant amine smell and are often toxic. As most of the tertiary amine(s) remains in the foam in the free state, the foam prepared has an undesirable smell and
10 gives off toxic vapors. Furthermore, the handling of tertiary amines during the manufacture of polyurethane foam demands specific precautions in order to meet safety standards.

 In order to overcome the above disadvantages,
15 the use has been proposed (paper by Savoca, Franson and Louie, UTECH'92 Conference Proceedings, p. 309-315 and US-A 4 433 170) of less volatile amines with a high molecular weight, however, the ratio by weight of the tertiary amine functional group with respect to the
20 weight of the molecule becomes low and the reactivity of the catalyst decreases. Furthermore, these amines are more expensive, they often still have an unpleasant smell and they often have a reactivity which is too different from that of standard amines, which is not
25 very acceptable to foam producers.

 Furthermore, it has also been proposed (paper by Diblitz and Hoell, UTECH'92 Conference Proceedings, p. 80-85) to attach the tertiary amine catalyst to free isocyanate functional groups. To this end, a tertiary
30 amine, for example a hydroxylated tertiary amine, which reacts with the isocyanate functional groups during the preparation of the polyurethane is added to the reaction mixture. However, in this case, it is still necessary to handle polluting amines at the stage of
35 preparation of the foam and precautions are still necessary to meet safety standards.

 The preparation of a polyurethane by reaction of at least one polyesterpolyol with at least one polyisocyanate is well known. This polyesterpolyol is

conventionally prepared by reaction of an acid reactant having a functionality at least equal to 2, such as adipic acid, with at least one polyol with a functionality equal to 2, such as diethylene glycol, subsequently denoted by P2, and at least one polyol with a functionality at least equal to 3, such as trimethylolpropane, glycerol or pentaerythritol, subsequently denoted by P3. FR-A-2 747 389 discloses the manufacture of specific polyesterpolyols, capable of being used in the manufacture of polyurethane foams, which do not exhibit fogging when they are used in the passenger compartment of a vehicle. According to this patent, the polyol P2 comprises monoethylene glycol and optionally a branched glycol with a functionality equal to 2 and the polyol P3 is a polyoxyalkylenated polyol which is, inter alia, obtained from triethanolamine or from triisopropanolamine. In the preparation of the polyurethane foams disclosed in FR-A-2 747 389, a separate tertiary amine catalyst, dibutylbenzylamine according to the examples, is still added.

According to the present invention, it has been found that, when the polyesterpolyol is prepared from at least one polyol P3 which is a polyoxyalkylenated polyol obtained by oxyalkylenation of a tertiary polyalkanolamine and when it is thus "amine", it is no longer essential, during the manufacture of the polyurethane foam, to separately add a tertiary amine as catalyst or, that to say the least, the amount of separate tertiary amine to be added is markedly reduced. This is because it has been found that the amine polyesterpolyol defined above has an autocatalytic effect, that is to say that it has both a reactive role and a catalyst role.

Throughout the text of the present patent application, the term "polyalkanolamine" has generically denoted an alkanolated amine which can be either a polyalkanolmonoamine or a polyalkanolpolyamine.

In a first embodiment, the tertiary polyalkanolamine is a polyamine, at least one amine group and preferably all the amine groups of which is (are) tertiary and is (are) substituted by identical or
5 different C₁-C₆ alkanol radicals.

In a second embodiment, the tertiary polyalkanolamine is a tertiary monoamine substituted by identical or different C₁-C₆ alkanol radicals.

Generally, according to the present invention,
10 it has been found that an amine polyesterpolyol in which is inserted at least one such polyoxyalkylenated polyalkanolamine had, by itself, a catalytic effect for the formation of polyurethane foams. It acts mainly on the foaming reaction in the presence of water and to a
15 certain extent on the reaction of the polyol with an isocyanate, known as gelling. Consequently, it is possible not to use any other amine catalyst, only a small amount of catalyst of the organometallic type optionally being able to be added in order to
20 accelerate the gelling reaction and to obtain a foam which does not collapse.

According to the invention, the tertiary amine is introduced during the polyesterification process into at least one polyesterpolyol used for the
25 manufacture of the polyurethane: it is thus included or inserted in the said polyesterpolyol; the result of this is that:

- the risks of evolution of tertiary amine during the manufacture of the polyurethane are avoided and, consequently, there is neither a problem of
30 odor nor a problem of toxicity on the foam production site; problems of pollution during the production of the foam are thus avoided and certain specific precautions for meeting safety standards do not have to be taken;
35
- foams are obtained which do not have an amine smell and are less toxic. In particular, a source of fogging when the foam is used in the passenger compartment of a motor vehicle is thus avoided

and, furthermore, when polyesterpolyols, such as those disclosed in FR-A-2 747 389, not comprising volatile cyclic dimers are employed, the foam does not result in any fogging.

5 The subject matter of the present invention is consequently a process for the manufacture of a polyurethane foam by reaction of at least one polyesterpolyol and of at least one polyisocyanate in the presence of a foaming agent and of a catalyzing agent, such a polyesterpolyol having been obtained
10 beforehand by reaction of an acid reactant A, comprising at least one aliphatic or aromatic polyacid with a functionality at least equal to 2, with at least one polyol P2 with a functionality equal to 2 and at
15 least one polyol P3 with a functionality at least equal to 3 and subsequently being denoted by AP2P3, characterized in that the catalyzing agent is at least partially composed of at least one amine polyesterpolyol AP2P3, in which at least a portion of
20 the polyol P3 is composed of at least one polyoxyalkylenated polyalkanolamine having at least one tertiary amine functional group, the alkanol radicals of the said polyalkanolamine being C₁-C₆ radicals, the alkylene oxide units being C₂-C₄ units and the
25 statistical mean of the number N of alkylene oxide units per polyoxyalkylated polyalkanolamine molecule being equal to $f \times x$, f being the number of hydroxyl functional groups per polyalkanolamine molecule and x being a number between 1 and 10 inclusive, preferably
30 between 2 and 5.

 The foaming agent is preferably water.


 According to the invention, preferably no amine catalyst other than the amine polyesterpolyol AP2P3 is used. However, it can be advantageous to also add a
35 nonamine catalyst of organometallic type, such as stannous octoate or dibutyltin dilaurate, in order to accelerate the gelling reaction of the isocyanate with the polyol and thus to obtain a more stable foam.

The polyalkanolamine can advantageously be a polyamine, all the amine functional groups of which are tertiary; however, in a particularly preferred way, the polyalkanolamine is a tertiary monoamine.

5 Preferably, the alkanol radicals of the polyalkanolamine(s) are C₂-C₃ radicals and the alkylene oxide units are taken from the group formed by ethylene oxide, propylene oxide and their mixtures, x being any number between 2 and 5 inclusive.

10 In the amine polyesterpolyol AP2P3, the molar ratio of the polyoxyalkylenated polyalkanolamine(s) to all the other polyols used for the reaction with the acid reactant A is preferably between 1/99 and 50/50, with greater preference between 3/97 and 10/90
15 (proportions in moles).

The polyol P2 comprises at least one glycol chosen from the group formed by monoethylene glycol, diethylene glycol and polyethylene glycols with an order greater than 2; it can also comprise at least one
20 branched glycol of formula:



in which formula:

- R₀ represents, independently in each [R₁R₀R₂] unit, a carbon atom, a C₆ alicyclic radical, a phenyl radical or a heterocyclic radical comprising 4 to
25 6 atoms which is saturated or unsaturated, the heteroatom being O or N;
- R₁ and R₂ represent, independently in each [R₁R₀R₂] unit and independently of one another, a hydrogen atom, a linear C₁-C₆ alkyl radical, a branched C₃-C₆ radical, a C₆ alicyclic radical or an aryl radical;
30
- with the proviso that, if R₀ is not a ring in any of the [R₁R₀R₂] units, R₁ and/or R₂ is (are)

different from H in at least one of the $[R_1R_0R_2]$ units;

- n is an integer between 1 and 8 (inclusive), with the proviso that, if n is greater than or equal to 4, the number of the carbon atoms in the combined R_0 , R_1 and R_2 radicals is greater than 8 in total.

Advantageously, the polyol P3 is composed entirely of one or more polyoxyalkylenated polyalkanolamine(s); however, it can also comprise at least one polyoxyalkylenated polyalkanol obtained by oxyalkylenation from a hydroxylated component, such as trimethylolethane, trimethylolpropane, ditrimethylolpropane, pentaerythritol, dipentaerythritol, glycerol, hexane-1,2,6-triol, butane-1,2,4-triol, sorbitol, tris(2-hydroxyethyl) isocyanurate and their mixtures, the number of alkylene oxide units per hydroxyl functional group of the polyalkanol preferably being, as a statistical mean, between 1 and 10 inclusive. The polyol P3 can also comprise non-oxyalkylenated alkanols, such as trimethylolethane, trimethylolpropane, ditrimethylolpropane, pentaerythritol, dipentaerythritol, glycerol, hexane-1,2,6-triol, butane-1,2,4-triol, sorbitol, tris(2-hydroxyethyl) isocyanurate and their mixtures.

The acid reactant A comprises at least one aliphatic or aromatic diacid preferably taken from the group formed by adipic acid and phthalic anhydride; it can also comprise at least one branched acid having a functionality greater than or equal to 2, which branched acid is preferably a dimer of an unsaturated C_{12} - C_{24} fatty acid. Use is advantageously made of a C_{18} fatty acid mono-, di- and trimer mixture comprising at least 70% by weight of dimer.

For the preparation of the amine polyesterpolyol AP2P3, the acid reactant A is conventionally reacted with a total amount of polyols P2 and P3 greater than stoichiometry, so as to obtain an amine polyesterpolyol AP2P3 comprising at least two free hydroxyl groups per molecule. The reaction is

generally carried out under an inert atmosphere, at a temperature of between 160 and 250°C, in the presence of an appropriate metallic or organometallic catalyst.

The polyurethane foam is prepared by reaction
5 of at least one polyesterpolyol and of at least one polyisocyanate by any known process, in particular by the so-called "one shot" process. The processes for the manufacture of polyurethanes are described in J.H. Saunders, K.C. Frisch, High Polymers, 1964, Vol. 26,
10 entitled "Polyurethanes Chemistry and Technology", published by "Interscience Publishers", or in G. Woods, 1982, "Flexible Polyurethane Foams: Chemistry and Technology", published by "Applied Science Publishers".

Other additives can also be introduced in a
15 known way into the reaction mixture, such as surfactants, polyols with a low molecular weight of less than or equal to 400 as chain extenders, foam-stabilizing agents, flame-retardant agents, pigments, dyes, fillers, stabilizers against aging or substances
20 having a fungistatic or bacteriostatic effect.

The polyisocyanate used can conventionally be at least one aromatic, aliphatic or heterocyclic polyisocyanate. Use is generally made of polyisocyanates or mixtures of polyisocyanates which
25 are readily available commercially, such as 2,4- and 2,6-toluylene diisocyanate (TDI) and their mixtures, diphenylmethane diisocyanates (MDI) or prepolymers resulting from the partial reaction of a polyisocyanate with a hydroxylated compound.

Another subject matter of the invention is an
30 amine polyesterpolyol AP2P3 capable of being used in the process defined above, the said polyesterpolyol being obtained by reaction of an acid reactant A, comprising at least one aliphatic or aromatic polyacid
35 with a functionality at least equal to 2, with at least one polyol P2 with a functionality equal to 2 and at least one polyol P3 with a functionality at least equal to 3, at least a portion of the polyol P3 being composed of:

- 5 - at least one polyoxyalkylenated tertiary
polyalkanolmonoamine, the alkanol radicals of the
said polyalkanolmonoamine being C₁-C₆ radicals, the
alkylene oxide units being C₂-C₄ units and the
10 statistical mean of the number of alkylene oxide
units per hydroxyl functional group of the
polyalkanolmonoamine being between 1 and 10
inclusive, the polyol P2 in this case not
comprising monoethylene glycol, or
15 - at least one polyoxyalkylenated polyalkanol-
polyamine having at least one tertiary amine
functional group, the alkanol radicals of the said
polyalkanolpolyamine being C₁-C₆ radicals, the
alkylene oxide units being C₂-C₄ units and the
20 statistical mean of the number N of alkylene oxide
units per polyalkanolpolyamine molecule being
equal to $f \times x$, f being the number of hydroxyl
functional groups per polyalkanolamine molecule
and x being a number between 1 and 10 inclusive;
in this case, preferably all the amine functional
groups of the polyamine are tertiary.

25 The alkanol radical of the polyalkanolamine(s)
is preferably a C₂-C₃ radical and the alkylene oxide
unit is taken from the group formed by ethylene oxide,
propylene oxide and their mixtures.


30 The molar ratio of the polyoxyalkylenated
polyalkanolamine to all the other polyols used for the
reaction with the acid reactant A is advantageously
between 1/99 and 50/50, preferably between 3/97 and
10/90 (proportions in moles).

35 When the polyalkanolamine is a
polyalkanolmonoamine, the polyol P2 advantageously
comprises at least one glycol chosen from the group
formed by diethylene glycol and polyethylene glycols
with an order greater than 2.

 When the polyalkanolamine is a
polyalkanolpolyamine, the polyol P2 advantageously
comprises at least one glycol taken from group formed

by monoethylene glycol, diethylene glycol and polyethylene glycols with an order greater than 2.

In all cases, the polyol P2 can also comprise at least one branched glycol of formula:



5

in which formula:

- R_0 represents, independently in each $[R_1R_0R_2]$ unit, a carbon atom, a C_6 alicyclic radical, a phenyl radical or a heterocyclic radical comprising 4 to 6 atoms which is saturated or unsaturated, the heteroatom being O or N;
- R_1 and R_2 represent, independently in each $[R_1R_0R_2]$ unit and independently of one another, a hydrogen atom, a linear C_1 - C_6 alkyl radical, a branched C_3 - C_6 radical, a C_6 alicyclic radical or an aryl radical;
- with the proviso that, if R_0 is not a ring in any of the $[R_1R_0R_2]$ units, R_1 and/or R_2 is (are) different from H in at least one of the $[R_1R_0R_2]$ units;
- n is an integer between 1 and 8 (inclusive), with the proviso that, if n is greater than or equal to 4, the number of the carbon atoms in the combined R_0 , R_1 and R_2 radicals is greater than 8 in total.

25 The polyol P3 is preferably composed entirely of one or more polyoxyalkylenated polyalkanolamine(s). However, the polyol P3 can also comprise at least one polyoxyalkylenated polyalkanol obtained by oxyalkylenation from a hydroxylated component, such as
 30 trimethylolethane, trimethylolpropane, ditrimethylolpropane, pentaerythritol, dipentaerythritol, glycerol, hexane-1,2,6-triol, butane-1,2,4-triol, sorbitol, tris(2-hydroxyethyl) isocyanurate and their mixtures, the number of alkylene oxide units per hydroxyl
 35 functional group in the molecule being, as a

statistical mean, between 1 and 10 inclusive. The polyol P3 can also comprise a non-oxyalkylenated polyol, such as trimethylolethane, trimethylolpropane, ditrimethylolpropane, pentaerythritol, dipenta-
5 erythritol, glycerol, hexane-1,2,6-triol, butane-1,2,4-triol, sorbitol, tris(2-hydroxyethyl) isocyanurate and their mixtures.

The acid reactant A advantageously comprises at least:

- 10 - one aliphatic or aromatic diacid preferably taken from the group formed by adipic acid and phthalic anhydride, and/or
- one branched acid having a functionality greater than or equal to 2, which branched acid is
15 preferably a dimer of an unsaturated C₁₂-C₂₄ fatty acid.

Another subject matter of the invention is the polyurethane foams obtained by the process defined above. These polyurethane foams can be used in all
20 their known uses. Mention may be made of their use in the furniture industry, for the manufacture of mattresses, cushions and coverings, for the manufacture of cushions and armrests in vehicles, and as absorbent for mineral oils. When they are rigid, they can be used
25 as thermal and sound insulators in buildings, as shockproofing in packages, as filters and, for their buoyancy, in shipbuilding. More particularly, a subject matter of the invention is the use of these foams for the production of components intended to equip the
30 passenger compartment of a motor vehicle.

Several examples of the implementation of the process according to the invention will be given below, purely by way of illustration and without limitation.

EXAMPLES

- 35 a) Preparation of ethoxylated triethanolamines (TEA)

Triethanolamine and an aqueous potassium hydroxide solution are introduced into a 6 liter reactor in the proportions given in Table I below. The

atmosphere and the contents of the reactor are dehydrated under a nitrogen atmosphere at 140°C. The reactor is closed and ethylene oxide is gradually introduced while maintaining the temperature at 150-
5 160°C and the pressure of the reactor at at most 3×10^5 Pa. The amount of ethylene oxide is given in Table I according to whether a triethanolamine comprising on average N = 3, 6, 9 or 12 mol of ethylene oxide, denoted respectively by TEA 3 AO, TEA 6 AO, TEA 9 AO or
10 TEA 12 AO, is desired. The reaction mixture is kept heated for 30 minutes and then cooled before opening the reactor.

TABLE I

	TEA 3 AO	TEA 6 AO	TEA 9 AO	TEA 12 AO
TEA, g	2120	1450	1090	880
KOH (50%), g	4	4	4	4
Ethylene oxide, g	1880	2560	2900	4000
OHN (mg KOH/g)	611	425	320	243
OHN = hydroxyl number				

15

Trimethylolpropane ethoxylated with 12 mol of ethylene oxide (TMP 12 AO) and glycerol ethoxylated with 12 mol of ethylene oxide (GLY 12 AO) are prepared analogously.

20

b) Preparation of polyesterpolyols

Adipic acid and the polyols are introduced, into an esterification reactor equipped with a fractionating column, in the molar proportions given in Table II, such that the finished product has a hydroxyl
25 number (OHN) equal to 60 ± 2 mg of KOH/g and an acid number (AN) < 2 mg of KOH/g. The mixture is heated to 220-230°C under a nitrogen atmosphere in the presence of 40 ppm of a tin-derived catalyst, such as "Fomrez SUL 11A", manufactured by "Witco Corporation". After
30 selective distillation of the water formed, the reaction is continued until the OHN and AN values defined in Table II are obtained.

TABLE II

	A	B	C	D	E	F	G	H	I	J	K	L	M
MEG ⁽¹⁾								60	60		57	64	62
DEG ⁽²⁾	94	94	93.5	93.5	93.5	94	94			89			
MPG ⁽³⁾								35	34.5		33	30	30
TMP ⁽⁴⁾	6												4
TEA ⁽⁵⁾		6								5			
PE ⁽⁶⁾												2	
TEA 3 EO			6.5										
TEA 6 EO				6.5									
TEA 9 EO					6.5					6	6	4	4
TEA 12 EO						6	6 ⁽⁷⁾		5.5				
TMP 12 EO								5					
GLY 12 EO											4		
OHN, mg	60	59.4	58.5	58.8	62	62	60.6	60	62	59	61.9	61	60.5
KOH/g													
AN, mg	1.5	0.6	1.4	1.8	1.2	1.3	1.3	1.3	0.9	0.9	0.9	1	1.1
KOH/g													
(1) Monoethylene glycol (2) Diethylene glycol (3) Monopropylene glycol (4) Trimethylolpropane (5) Triethanolamine (6) Pentaerythritol (7) Demineralized													

In this table, the product A is a polyadipate
 5 sold by Witco Corporation under the name "Fomrez 60
 LV", which is prepared without use of ethoxylated
 polyalkanolamine; the product B is prepared from
 nonethoxylated triethanolamine. The ethoxylated
 triethanolamine comprising a small amount of potassium
 10 without removal at the end was used for all the
 products C, D, E, F, I, J, K, L and M; for the product
 G, the potassium was removed by addition of 2% of
 magnesium silicate (sold by Hoechst under the name
 "Ambosol C"), stirring for 2 hours at 100-110°C with

nitrogen at the surface and then filtering through paper.

c) Preparation of the foams

One of the polyesters A to M in Table II is
5 mixed manually using a rotary stirrer with 80/20
toluylene diisocyanate (TDI), which is a mixture of
2,4-TDI and 2,6-TDI in an 80/20 ratio. The amount of
polyisocyanate employed is stoichiometric with respect
to all the ingredients capable of reacting with the
10 isocyanate functional group (index 100).

The mixture comprises water and a surfactant:
"Niax silicon surfactant SE 232 or L 534", sold by the
company "Witco Corporation".

The various formulations per 100 parts by
15 weight of polyester necessary in order to obtain a foam
with a density equal to approximately 30 kg/m³ are
given in Table III below.

In the case of the polyester A, two tests were
carried out:

- 20 - one (A1) in the presence of two tertiary amines
conventionally used as catalyst: N-ethylmorpholine
(NEM) and hexadecyldimethylamine (HDDMA), and
- the other (A2) in the absence of catalyst.

With the polyester H, a formulation with
25 another conventional amine catalyst: DB =
dimethylbenzylamine (Test H1), and a noncatalyzed
formulation (Test H2) are also given.

Tests B, C1, D, E1, F1, G, I, J and K were
carried out without addition of separate tertiary amine
30 catalysts. In Tests C2, E2, F2, L and M1, an
organometallic catalyst, stannous octoate, was added.
In Test M2, a small amount of tertiary amine was
introduced.

The cream time (time necessary for the
35 beginning of the foaming) and the rise time (time
necessary in order to obtain the end of the foaming)
were measured. The stability of the foam was also
evaluated by assessing the collapse at the end of rise.
The quality of the foam was also evaluated after

maturing for 30 min at 90-100°C, followed by 24 hours at 23-25°C. The visual appearance is given, as well as the number of cells per cm when the foam is satisfactory.

002274-202260

TABLE III

Formulation	A1	A2	B	C1	C2	D	E1	E2	F1	F2	G	H1	H2	I	J	K	L	M1	M2
Water	3.8	3.8	3.8	3.8	3.8	3.8	3.8	3.8	3.8	3.8	3.8	3.8	3.8	3.8	3.8	3.8	3.8	3.8	3.8
Niav SE 232	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1	1
Niav L 534	-	-	-	-	-	-	-	-	-	-	-	1	1	-	-	-	1	1	1
NEM	1.8	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
HDDMA	0.1	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
DB ⁽¹⁾	-	-	-	-	-	-	-	-	-	-	-	1.3	-	-	-	-	-	-	0.6
Stannous octoate	-	-	-	-	0.05	-	-	0.05	-	0.05	-	-	-	-	-	-	0.05	0.05	-
Cream time, s	12	240	85	20	16	18	15	15	15	12	15	16	200	17	14	15	20	20	16
Rise time, s																			
Collapse at the end	83	>>300	>300	125	120	100	96	87	98	90	95	78	>>300	112	95	113	110	115	85
Appearance of the foam	none	total	very high	high	slight cracked	slight cracked	slight cracked	none	slight cracked	none	slight cracked	none	total	slight cracked	none	none	none	none	none
Number of cells/cm	good	na*	high	hollow	-	-	-	good	-	good	-	good	na*	-	good	good	good	good	good
	20-22	-	-	-				20-22		20-22		20-22	-		20-22	20-22	20-22	20-22	20-22
Amine smell	strong	none	none	none	none	none	none	none	none	none	none	strong	none	none	none	none	none	none	slight

(1) Dimethylbenzylamine

* not applicable: there is collapse of the foam

These tests show that the polyesterpolyols C, D, E, F, G, I, J, K, L and M which comprise polyethoxylated triethanolamine make it possible to obtain, without it being necessary to add a separate tertiary amine catalyst, foams having a reactivity similar to that of the standard formulation A1 in which a separate catalyst composed of two tertiary amines was used. Furthermore, the foams obtained do not have an amine smell perceptible to the nose.

- 10 The tests carried out with the polyesterpolyols J and K show that it is possible to do without amine catalyst. Comparison of Tests C1 and C2, E1 and E2, and F1 and F2 show [sic] that when the gelling reaction is not sufficiently catalyzed, addition of a small amount of organometallic catalyst, which has the advantage of not introducing free amine, makes it possible to obtain a foam which does not collapse. Tests L and M1 confirm this behavior. Test M2 shows that it is optionally possible to obtain a good foam by using a tertiary amine but in a markedly lower amount than in a conventional formulation (Tests A1 and H1).

Comparison of the foams obtained with the polyesterpolyols F1 and G shows that the potassium is not the cause of the observed catalytic effect.

- 25 Test B shows that the catalytic effect according to the invention is not produced when the polyesterpolyol incorporates only a nonethoxylated triethanolamine.

- 30 Tests A2 and H2 show that the catalytic effect according to the invention is not produced when no catalyst is employed at the time of mixing and when a polyesterpolyol obtained without incorporation of ethoxylated triethanolamine is used.

CLAIMS

1. Process for the manufacture of a polyurethane foam by reaction of at least one polyesterpolyol and of at least one polyisocyanate in the presence of a foaming agent and of a catalyzing agent, such a polyesterpolyol having been obtained beforehand by reaction of an acid reactant A, comprising at least one aliphatic or aromatic polyacid with a functionality at least equal to 2, with at least one polyol P2 with a functionality equal to 2 and at least one polyol P3 with a functionality at least equal to 3 and subsequently being denoted by AP2P3, characterized in that the catalyzing agent is at least partially composed of at least one amine polyesterpolyol AP2P3, in which at least a portion of the polyol P3 is composed of at least one polyoxyalkylenated polyalkanolamine having at least one tertiary amine functional group, the alkanol radicals of the said polyalkanolamine being C_1 - C_6 radicals, the alkylene oxide units being C_2 - C_4 units and the statistical mean of the number N of alkylene oxide units per polyoxyalkylated polyalkanolamine molecule being equal to $f \times x$, f being the number of hydroxyl functional groups per polyalkanolamine molecule and x being a number between 1 and 10 inclusive.
2. Process according to Claim 1, characterized in that the foaming agent is water.
3. Process according to Claim 2, characterized in that the amine polyesterpolyol(s) AP2P3 is (are) the only amine catalyst(s) of the catalyst agent.
4. Process according to either of Claims 2 and 3, characterized in that the catalyst agent comprises, in addition to the amine polyesterpolyol(s) AP2P3, at least one catalyst of organometallic type.
5. Process according to one of Claims 1 to 4, characterized in that the polyalkanolamine at least partially constituting the polyol P3 is a polyamine.

6. Process according to Claim 5, characterized in that all the amine functional groups of the polyamine are tertiary.


7. Process according to one of Claims 1 to 6, characterized in that the polyalkanolamine at least partially constituting the polyol P3 is a tertiary monoamine.

8. Process according to one of Claims 1 to 7, characterized in that the alkanol radicals of the polyalkanolamine(s) are C₂-C₃ radicals and the alkylene oxide units are taken from the group formed by ethylene oxide, propylene oxide and their mixtures, x being a number between 2 and 5 inclusive.

9. Process according to one of Claims 1 to 7, characterized in that, in the amine polyesterpolyol AP2P3, the molar ratio of the polyoxyalkylenated polyalkanolamine(s) to all the other polyols used for the reaction with the acid reactant A is between 1/99 and 50/50.

10. Process according to one of Claims 1 to 9, characterized in that the polyol P2 comprises at least one glycol chosen from the group formed by monoethylene glycol, diethylene glycol and polyethylene glycols with an order greater than 2.

11. Process according to one of Claims 1 to 10, characterized in that the polyol P2 comprises at least one branched glycol of formula:



in which formula:

- R₀ represents, independently in each [R₁R₀R₂] unit, a carbon atom, a C₆ alicyclic radical, a phenyl radical or a heterocyclic radical comprising 4 to 6 atoms which is saturated or unsaturated, the heteroatom being O or N;

- R_1 and R_2 represent, independently in each $[R_1R_0R_2]$ unit and independently of one another, a hydrogen atom, a linear C_1 - C_6 alkyl radical, a branched C_3 - C_6 radical, a C_6 alicyclic radical or an aryl radical;
5
 - with the proviso that, if R_0 is not a ring in any of the $[R_1R_0R_2]$ units, R_1 and/or R_2 is (are) different from H in at least one of the $[R_1R_0R_2]$ units;
 - 10 - n is an integer between 1 and 8 (inclusive), with the proviso that, if n is greater than or equal to 4, the number of the carbon atoms in the combined R_0 , R_1 and R_2 radicals is greater than 8 in total.
12. Process according to one of Claims 1 to 10, characterized in that the polyol P3 is composed
15 entirely of one or more polyoxyalkylenated polyalkanolamine(s).
13. Process according to one of Claims 1 to 11, characterized in that the polyol P3 comprises at least
20 one polyoxyalkylenated polyalkanol obtained by oxyalkylenation from a hydroxylated component taken from the group formed by trimethylolethane, trimethylolpropane, ditrimethylolpropane, pentaerythritol, dipentaerythritol, glycerol, hexane-1,2,6-triol,
25 butane-1,2,4-triol, sorbitol, tris(2-hydroxyethyl) isocyanurate and their mixtures, the number of alkylene oxide units per polyoxyalkylenated polyalkanol molecule being, per hydroxyl functional group, as a statistical mean, between 1 and 10
30 inclusive.
14. Process according to one of Claims 1 to 13, characterized in that the acid reactant A comprises at least one diacid taken from the group formed by adipic acid and phthalic anhydride.
- 35 15. Process according to one of Claims 1 to 14, characterized in that the acid reactant A comprises at least one branched acid having a functionality greater than or equal to 2.

16. Process according to Claim 15, characterized in that the branched acid is a dimer of an unsaturated C₁₂-C₂₄ fatty acid.

17. Amine polyesterpolyol AP2P3 capable of being
5 used in the process according to one of Claims 1 to 16, the said polyesterpolyol AP2P3 being obtained by reaction of an acid reactant A, comprising at least one aliphatic or aromatic polyacid with a functionality at least equal to 2, with at least one polyol P2 with a
10 functionality equal to 2 and at least one polyol P3 with a functionality at least equal to 3, characterized in that at least a portion of the polyol P3 is composed of at least one polyoxyalkylenated tertiary polyalkanolmonoamine, the alkanol radicals of the said
15 polyalkanolmonoamine being C₁-C₆ radicals, the alkylene oxide units being C₂-C₄ units and the statistical mean of the number of alkylene oxide units per hydroxyl functional group of the polyalkanolmonoamine molecule being between 1 and 10 inclusive, the polyol P2 not
20 comprising monoethylene glycol.

18. Amine polyesterpolyol AP2P3 capable of being used in the process according to one of Claims 1 to 16, the said amine polyesterpolyol AP2P3 being obtained by reaction of an acid reactant A, comprising at least one
25 aliphatic or aromatic polyacid with a functionality at least equal to 2, with at least one polyol P2 with a functionality equal to 2 and at least one polyol P3 with a functionality at least equal to 3, characterized in that at least a portion of the polyol P3 is composed
30 of at least one polyoxyalkylenated polyalkanolamine having at least one tertiary amine functional group, the alkanol radicals of the said polyalkanolpolyamine being C₁-C₆ radicals, the alkylene oxide units being C₂-C₄ units and the statistical mean of the number N of
35 alkylene oxide units per polyalkanolpolyamine molecule being equal to $f \times x$, f being the number of hydroxyl functional groups per polyalkanolamine molecule and x being a number between 1 and 10 inclusive.

19. Amine polyesterpolyol AP2P3 according to Claim 18, characterized in that all the amine functional groups of the polyamine are tertiary.


20. Amine polyesterpolyol AP2P3 according to one of Claims 17 to 19, characterized in that the alkanol radical of the polyalkanolamine(s) is a C₂-C₃ radical and the alkylene oxide unit is taken from the group formed by ethylene oxide, propylene oxide and their mixtures.

21. Amine polyesterpolyol AP2P3 according to one of Claims 17 to 20, characterized in that the molar ratio of the polyoxyalkylenated polyalkanolamine to all the other polyols used for the reaction with the acid reactant A is between 1/99 and 50/50.

22. Amine polyesterpolyol AP2P3 according to Claim 17, characterized in that the polyol P2 comprises at least one glycol chosen from the group formed by diethylene glycol and polyethylene glycols with an order greater than 2.

23. Amine polyesterpolyol AP2P3 according to Claim 18, characterized in that the polyol P2 comprises at least one glycol taken from group formed by monoethylene glycol, diethylene glycol and polyethylene glycols with an order greater than 2.

24. Amine polyesterpolyol AP2P3 according to one of Claims 17 to 23, characterized in that the polyol P2 comprises at least one branched glycol of formula:



in which formula:

- 30 - R₀ represents, independently in each [R₁R₀R₂] unit, a carbon atom, a C₆ alicyclic radical, a phenyl radical or a heterocyclic radical comprising 4 to 6 atoms which is saturated or unsaturated, the heteroatom being O or N;

- R_1 and R_2 represent, independently in each $[R_1R_0R_2]$ unit and independently of one another, a hydrogen atom, a linear C_1 - C_6 alkyl radical, a branched C_3 - C_6 radical, a C_6 alicyclic radical or an aryl radical;
 - with the proviso that, if R_0 is not a ring in any of the $[R_1R_0R_2]$ units, R_1 and/or R_2 is (are) different from H in at least one of the $[R_1R_0R_2]$ units;
 - n is an integer between 1 and 8 (inclusive), with the proviso that, if n is greater than or equal to 4, the number of the carbon atoms in the combined R_0 , R_1 and R_2 radicals is greater than 8 in total.
25. Amine polyesterpolyol AP2P3 according to one of Claims 17 to 24, characterized in that the polyol P3 is composed entirely of one or more polyalkanolamine(s).
26. Amine polyesterpolyol AP2P3 according to one of Claims 17 to 24, characterized in that the polyol P3 comprises at least one polyoxyalkylenated polyalkanol obtained by oxyalkylenation from a hydroxylated component taken from the group formed by trimethylolethane, trimethylolpropane, ditrimethylolpropane, pentaerythritol, dipentaerythritol, glycerol, hexane-1,2,6-triol, butane-1,2,4-triol, sorbitol, tris(2-hydroxyethyl) isocyanurate and their mixtures, the number of alkylene oxide units per hydroxyl functional group being, as a statistical mean, between 1 and 10 inclusive.
27. Amine polyesterpolyol AP2P3 according to one of Claims 17 to 26, characterized in that the acid reactant A comprises at least one diacid taken from the group formed by adipic acid and phthalic anhydride.
28. Amine polyesterpolyol AP2P3 according to one of Claims 17 to 27, characterized in that the acid reactant A comprises at least one branched acid having a functionality greater than or equal to 2.
29. Amine polyesterpolyol AP2P3 according to Claim 28, characterized in that the branched acid is a dimer of an unsaturated C_{12} - C_{24} fatty acid.

30. Polyurethane foam obtained by the process according to one of Claims 1 to 16.

31. Use of the foam according to Claim 30 for the production of elements intended to equip the passenger
5 compartment of a motor vehicle.

ABSTRACT

10 The invention concerns a method for making a
polyurethane foam by reacting at least a polyester
polyol with at least a polyisocyanate in the presence
15 of a foaming agent and a catalytic agent, such a
polyester polyol having been previously obtained by
reacting a reactive acid A comprising at least an
20 aliphatic or aromatic polyacid with functionality not
less than 2 with at least a polyol P2 with
25 functionality equal to 2 and at least an aliphatic or
aromatic polyacid with functionality not less than 2
with at least a polyol P2 with functionality equal to
30 2 and at least a polyol P3 with functionality not
less than 3, being thereafter called AP2P3, wherein
35 the catalytic agent at least partly consists of at
least one amine polyester polyol AP2P3, wherein at
least part of polyol P3 consists of at least a
40 polyoxyalkylene polyalkanolamine having at least a
tertiary amine function, the alkanol radicals of said
45 polyalkanolamine being C1-C6, the alkylene oxide
units being C2-C4 and the statistical mean of the
number N of alkylene oxide units per polyoxyalkylene
50 polyalkanolamine being equal to $f \times X$, f being the
number of hydroxyl functions per polyalkanolamine
55 molecule and X being a number ranging between 1 and
10, inclusively.

Declaration and Power of Attorney for Patent Application

As the below named inventors, We hereby declare that:

Our residences, post office addresses and citizenship are as stated below next to our names;
We believe we are the original, first and joint inventors of the invention which is described
and claimed and for which a patent is sought on the invention entitled:

**PROCESS FOR THE MANUFACTURE OF POLYURETHANE FOAM, AMINE
POLYESTERPOLYOL USED IN THIS PROCESS AND FOAM OBTAINED**

the specification of which (check one)

- ☒ is attached hereto,
☐ was filed on _____ and accorded serial number _____ and
was amended on _____.

We hereby state that we have reviewed and understand the contents of the above-identified
specification, including the claims, as amended by any amendment referred to above.

We acknowledge the duty to disclose information which is material to the examination of
this application in accordance with 37 CFR § 1.56(a).

We hereby claim foreign priority benefits under 35 USC §119 or §365 of any foreign
application(s) for patent or inventor's certificate, or §365 of any PCT international
application which designated at least one country other than the United States, listed below
and have also identified below, by checking the box, any foreign application for patent or
inventor's certificate having a filing date before that of the application on which priority is
claimed:

Prior Foreign Application(s):

Number	Country	Day/Month/Year	Priority Claimed
PCT/FR99/01176	PCT	18 May 1999	YES
98 06806	France	29 May 1998	YES

We hereby claim the benefit under 35 USC §119(e) of any United States provisional
application(s) listed above:

Application Number	Filing Date
--------------------	-------------

We hereby claim the benefit under 35 USC §120 of any United States application(s), or any
§365^o of any PCT international application designating the United States, listed below and,
insofar as the subject matter of each of the claims of this application is not disclosed in the
prior United States application in the manner provided by the first paragraph of 35 USC
§112, We acknowledge the duty to disclose material information as defined in 37 CFR
§1.56 which became available between the filing date of the prior application and the
national or PCT international filing date of this application:

Prior U.S. Applications:

Serial No.	Filing Date	Status (patented, pending, abandoned)
------------	-------------	---------------------------------------

We hereby appoint the following attorney's and/or agent(s) to prosecute this application and to transact all business in the Patent and Trademark Office connected therewith: **Raymond D. Thompson - Reg. No. 30,695, Daniel Reitenbach - Reg. No. 30,970, and Shirley S. Ma - Reg. No. 44,216.**

Address all telephone calls to: **Shirley S. Ma of Crompton Corporation** at (203)573-3313.

Address all correspondence to: **CROMPTON CORPORATION**
199 Benson Road
Middlebury, CT 06749

We hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

(1)	FULL NAME OF INVENTOR	GHESQUIERE, DENIS		
	CITIZENSHIP	FRENCH		
	RESIDENCE ADDRESS	29, rue Madeleine Fosse, F-27370, Tourville la Campagne, France		
	POST OFFICE ADDRESS	Same as Above		
	SIGNATURE		DATE	

(2)	FULL NAME OF INVENTOR	DUMONT, RéMY		
	CITIZENSHIP	FRENCH		
	RESIDENCE ADDRESS	37, rue du Point du jour, F-27370 Thuit Signol, France		
	POST OFFICE ADDRESS	Same as Above		
	SIGNATURE		DATE	

0022764202250